


Condition 4 : Construction Method Section

36 Whitehill Lane, Gravesend DA12 5LY



Paving Units & Jointing

Setts are bonded on a concrete/mortar mix laying course. Pointed with either traditional mortar or jointing compound

Bounded Laying Course (50 mm)

Concrete/mortar bed laying course. It should be a coarse mix (using ballast/grit sand) to provide additional strength.

Sub Base (150 mm)

Sub base of compacted Type 1 MOT hardcore. Depth will depend on the stability and firmness of the substrate. Depth should be a minimum of 150 mm to ensure a stable sub base.

Substrate

The substrate must be firm and stable. Where required, if the ground is too soft, a deeper excavation may be required (with the additional depth being filled with a deeper and fully compacted hardcore sub base).